



Rue de Lonnoix, 3
6880 Bertrix
+32 (0) 61 41 50 52
www.sealuxsa.eu
info@sealuxsa.eu

SEALUX Forme A DIN 7603 Cuivre Recuit

Annealed copper **Form A gaskets and washers** are used to create a static seal. They are corrosion-resistant and conform well to irregular surfaces.

Condition	Tensile Strength (MPA)	Yield Strength at 0,2% (MPA)	Elongation (A %)	Vickers Hardness
Annealed	220	≤ 120	25	40-65

Dimensional Table (mm) :

d1	M4	M5	M6	M6	M6.5	M8	M8	M8	M8	M8	M8	M8	M8	M10	M10	M10	M10	M10	M12
d2	8	9	10	12	9.5	11	11.5	12	14	14	15	22	13	14	14	16	16	16	16
h1	1	1	1	1	1	1	1	1	1	1.5	1.5	1.5	1	1	1.5	1	1.5	1	1
d1	M12	M12	M12	M14	M14	M14	M14	M16	M16	M17	M18	M18	M19	M20	M20	M22	M22	M23	
d2	16	18	24	18	20	22	22	20	22	21	22	24	26	24	26	27	29	28	
h1	1.5	1.5	2	1.5	1.5	1.5	2	1.5	1.5	1.5	1.5	1.5	2	1.5	1.5	1.5	1.5	2	
d1	M24	M24	M25	M27	M27	M28	M30	M30	M48										
d2	29	32	35	32	35	34	36	36	55										
h1	2	2	2	2	2	2	2	2.5	2										

